



# TECHNICAL INFORMATION - RUBBER

## AVK GATE VALVES

### RUBBER SPECIFICATIONS:

Rubber quality	EUW-70	EUW-75	EUW-80	EAW-70	EAW-75	EDK-55	EDK-70	EDK-80
Rubber type	EPDM	EPDM	EPDM	EPDM	EPDM	EPDM	EPDM	EPDM
Hardness (ShA)	70	76	80	70	76	56	70	80
Tensile strength (Mpa)	14.0	15.0	13.0	12.0	10.1	10.0	13.0	13.0
Elongation at break (%)	370	353	350	400	361	500	300	290
Density (g/cm <sup>3</sup> )	1.10	1.18	1.21	1.23	1.31	1.19	1.12	1.17
Temperature range in dry atmospheric air:								
Minimum temperature (°C *)	-40	-40	-40	-40	-40	-40	-40	-40
Maximum temperature (°C *)	+120	+120	+120	+120	+120	+120	+120	+120
Compression set DIN 53517, 24 hours /70°C (%)								
	15.0	12.0	15.0	15.0	12.5	12.0	8.0	17.0
Characteristics:								
Wear resistance	3	3	3	2	2	2	3	3
Tear resistance	4	4	4	3	3	2	3	3
Resistance to weather and ozone	4	4	4	4	4	4	4	4
Resistance to hydrolysis (water and steam)	4	4	4	4	4	4	4	4
Resistance to chemicals (acids/bases)	3	3	3	3	3	3	3	3
Resistance to mineral oil and gas	0	0	0	0	0	0	0	0
Permeability	1	1	1	1	1	1	1	1

0: Low 1: Limited 2: Medium 3: Considerable 4: High

Rubber quality	NDG-80	NGW-70	SAK-70
Rubber type	NBR	NBR	SBR
Hardness (ShA)	80	70	70
Tensile strength (Mpa)	18.0	15.0	15.0
Elongation at break (%)	220	320	300
Density (g/cm <sup>3</sup> )	1.26	1.23	1.17
Temperature range in dry atmospheric air:			
Minimum temperature (°C *)	-35	-40	-50
Maximum temperature (°C *)	+110	+110	+100
Compression set DIN 53517, 24 hours /70°C (%)			
	8.0	8.0	13.0
Characteristics:			
Wear resistance	3	3	4
Tear resistance	3	3	3
Resistance to weather and ozone	3	3	3
Resistance to hydrolysis - water/steam	3	3	3
Resistance to chemicals - acids/bases	2-3	2-3	2
Resistance to mineral oil and gas	4	4	0
Permeability	4	4	2

0: Low 1: Limited 2: Medium 3: Considerable 4: High

### Approvals/remarks:

EUW-70: KTW D1/D2, W270, WRAS (60°C), ACS XP P 41-250, AS/NZS 4020, NSF-61, EN 681-1, AS 1646-2007, Önorm B5014

EUW-75: KTW D1/D2, W270, WRAS (50°C), ACS XP P 41-250, EN 681-1

EUW-80: KTW D1/D2, W270, WRAS, ACS XP P 41-250, EN 681-1

EAW-70: KTW D1/D2 (warm 60°C), W270

EAW-75: KTW D1/D2, W270

EDK-55: ACS XP P41-250

EDK-70: KTW D1/D2 (60°C), ACS XP P 41-250, CSN 75 7111, NBN S 29003, Hydrochek

EDK-80: KTW D1/D2

NGW-70: EN 682 type GBL, KTW D2

SAK-70: UL-listed 22.06.1993

Above mentioned results are based on laboratory tests and must be evaluated for specific articles and applications.

Fire may create small amounts of hydrogen sulphide, and carbon dioxide. Disposal by incineration in compliance with local regulations.

\*) Different temperature restrictions may apply to valves due to bonding between metal and rubber